

Mechanical Properties

| Steel group | Tensile Strength | Yield Strength min. | Elongation |
|--------------------|-------------------------|--------------------------------|-------------------|
| | MPa | MPa | % |
| Fe 330 | 330÷520 | 210 | 22 |
| S195T | 320÷520 | 195 | 20 |