

Chemical Composition (%)

Steel group	C max	Mn max	Si max	S max	P max	Cr max	Cu max	Mo max	Ni max	Ti max	V max
P215NL	0.15	0.40÷1.20	0.35	0.020	0.025	0.30	0.30	0.08	0.30	0.04	0.02
P265NL	0.2	0.60÷1.40	0.4	0.020	0.025	0.30	0.30	0.08	0.30	0.04	0.02
Grade 6	0.30	0.29÷1.06	0.10 min	0.025	0.025						