

Mechanical Properties

Steel group	Tensile Strength	Yield Strength min.	Elongation min.	Min. impact energy	
	MPa	MPa	%	J	°C
P215NL	360÷480	215	25	40	-40
P265NL	410÷570	265	24	40	-40